

技术数据书



热缩套管

(无卤素)

产品编号: 2S1 (600V)
2S2 (300V)

P. LEO & CO LTD

P.O. Box 175 Fo Tan, Shatin, Hong Kong.
Telephone : (852) 2604-8222 * Facsimile : (852) 2693-2093
E-mail : sales@pleo.com * Web Site : http://www.pleo.com



UL FILE #E176865

安规标准: UL224 VW-1, C-UL CSA C 22.2 OFT

产品编号: 2S1yy-xx.x & 2S2yy-xx.x (yy - 说明套管颜色 例如 BK=黑色 WH=白色 YE=黄色 RD=红色 GR=绿色 BL=蓝色; xx.x -说明扩大内径由 1mm x 50mm)

说明: **BC TUBE** 2S1 & 2S2 系列 无卤环保阻燃热缩套管采用优质高聚物,经科学配方、机械共混成高聚物合金我,产品成型后经电子加速器辐照交联、连续扩张而成,产品具有环保、柔软、阻燃、收缩快、性能稳定等优点,广泛应用于电线连接、焊点保护、电线端部、线束及电子元器件的防护和绝缘处理;健身器材零部件和钢结构表面防护;相关产品的防锈、防腐处理;电线和其他产品的标识等。

特点:

- 1、 八大有害元素、卤素元素通过 SGS 检测;
- 2、 不含有机锡化物(三丁基锡类/三苯基锡类),石棉(asbestos)、烟雾剂(Azo compounds)及限制其释放的物质-甲醛;
- 3、 适用范围: -55°C-125°C;
- 4、 起始收缩温度 70°C,超薄型完全收缩温度 110°C,普通型完全收缩温度 120°C,收缩率±5%;
- 5、 柔软、阻燃;
- 6、 规格齐全, ϕ 0.8~ ϕ 18.0,并可订制特殊规格;
- 7、 使用方便,用烘箱和热风枪即可收缩;
- 8、 环保性能符合 Sony 与欧盟 RoHs 等环保标准;
- 9、 标准颜色 黑、白、红、黄、绿、蓝为基本颜色,常备库存,其他颜色不备库存,需定做。

性能特性:

		性能	测试方法	性能
物理特性	拉伸强度 (MPa)		ASTM D2671	≥10.4
	断裂伸长率 (%)		ASTM D2671	≥200
	热老化后拉伸强度 (MPa)		UL224 158°C x 168hr	≥7.3
	热老化后断裂伸长率 (%)		UL224 158°C x 168hr	≥100
	耐热冲击		UL224 250°C x 4hr	不发粘 不龟裂
电气特性	击穿强度		IEC243	≥15 KV/mm
	耐压	300V	UL224	1500V 不击穿
		600V	UL224	2500V 不击穿
体积电阻率(Ω .cm)		IEC93	> 1 x 10 ¹⁴ Ω *cm	
化学特性	抗腐蚀性		UL224 158°C x 168hr	合格
	铜兼容性		UL224 158°C x 168hr	合格
	阻燃性		UL224	VW-1

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or the inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection there with.

No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of Seller and manufacturer.

以上仅供参考, 如与英文版有歧异之处, 一切内容以英文版为准



產品規格

尺寸		收缩前	收缩后		标准包装
Inch	mm	内径 mm	内径 最大 mm	壁厚 标清 mm	每盘长度 米/盘
3/64	0.8	1.1±0.2	0.50	0.22	200
1/16	1.0	1.5±0.2	0.65	0.28	200
	1.5	2.0±0.2	0.85	0.32	200
3/32	2.0	2.5±0.2	1.00	0.35	200
	2.5	3.0±0.2	1.30	0.38	200
1/8	3.0	3.5±0.2	1.50	0.40	200
	3.5	4.0±0.2	1.80	0.42	200
	4.0	4.5±0.2	2.00	0.45	200
3/16	4.5	5.0±0.2	2.30	0.50	200
	5.0	5.5±0.2	2.5	0.55	100
1/4	6.0	6.5±0.2	3.0	0.55	100
5/16	7.0	7.5±0.3	3.5	0.55	100
	8.0	8.5±0.3	4.0	0.60	100
3/8	9.0	9.5±0.3	4.5	0.60	100
	10.0	10.5±0.3	5.0	0.60	100
	11.0	11.5±0.3	5.5	0.60	100
1/2	12.0	12.5±0.3	6.0	0.60	100
	13.0	13.5±0.3	6.5	0.65	100
	14.0	14.5±0.3	7.0	0.65	100
5/8	15.0	15.5±0.4	7.5	0.70	100
	16.0	16.5±0.4	8.0	0.70	100
	17.0	17.5±0.4	8.5	0.70	100
3/4	18.0	19.0±0.5	9.0	0.80	100
	20.0	21.0±0.5	10.0	0.80	100
	22.0	23.0±0.5	11.0	0.80	100
1	25.0	26.0±0.5	12.5	0.90	50
	28.0	29.0±0.5	14.0	0.90	50
1-1/4	30.0	31.5±1.0	15.0	0.95	50
	35.0	36.5±1.0	17.5	1.00	50
1-1/2	40.0	41.5±1.0	20.0	1.00	50
	45.0	46.5±1.0	22.5	1.00	25
2	50.0	≥ 50	25.0	1.00	25
	60.0	≥ 60	31.0	1.30	25
	70.0	≥ 70	36.0	1.30	25
3	80.0	≥ 80	41.0	1.46	25
	90.0	≥ 90	46.0	1.46	25
4	100.0	≥ 100	51.0	1.46	25
5	120.0	≥ 120	61.0	1.56	25
6	150.0	≥ 150	76.0	1.56	25
7	180.0	≥ 180	91.0	1.56	25



® Phobbin ® BCwire ® BCmica ® BCtube ® is P. Leo & Co., Ltd. registered trade mark

Important Notice to Purchase

All Statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and the following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace such quantity of the product of the product proved to be defective. Neither seller nor manufacturer shall be liable for any injury loss or damage direct or consequential arising out of the use of or the inability to use the product. Before using users shall determine the suitability of the product for their intended uses and users assume all risk and liability whatsoever in connection there with.

No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of Seller and manufacturer.

以上仅供参考，如与英文版有歧异之处，一切内容以英文版为准

